



Product Information BAEROSTAB NT 340 RF

Description	Type Appearance	Ca/Zn stabiliser liquid
Performance / Application	BAEROSTAB NT 340 RF is a low odour non-toxic Ca/Zn stabiliser. BAEROSTAB NT 340 RF has been developed for the extrusion of crystal clear and pigmented flexible PVC. BAEROSTAB NT 340 RF is free from TNPP. BAEROSTAB NT 340 RF offers in combination with epoxy plasticiser BAEROSTAB LSA (2 - 5 phr) excellent static and dynamic heat stability and plate-out-free processing. Recommended dosage: 1 - 2 phr. Depending on conditions, the self-lubricating properties of BAEROSTAB NT 340 RF can be backed-up by addition of some external lubricant.	
Approval	BAEROSTAB NT 340 RF is approved for food contact applications in most countries. Upon customer request , Baerlocher product safety department will prepare an updated statement.	
Storage	Dry storage at normal temperature (15- 40°C) is recommended. Once opened packaging should be firmly closed.	

NOTICE: Although the information and recommendations contained in this document (hereinafter "Information") are presented in good faith and believed to be correct at the date of their publication, BAERLOCHER makes no representations or warranties as to the completeness or accuracy of Information. Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes prior to their use. In no event, will BAERLOCHER be responsible or liable for any loss of profits, lost goodwill, direct, special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or intellectual property right, and BAERLOCHER makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights.

No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers.

3361010e#-NT_BS NT 340 RF_MB 102-104 _BIT Rev. – 13.11.13